



CETCRETE LATEX

1317

Latex based polymer component for waterproofing

Description:

CETCRETE LATEX is acrylic co-polymer latex based dispersion with extraordinary favorable characteristics when as polymer component in hydraulically setting mortars

Advantages:

- Strength of adhesion to the base is distinctly improved.
- The compressive and flexural strength is increased compared with the reference mix.
- Water absorption is reduced, thus providing waterproofing properties.
- The water retention value of the mortar is improved this involving less risk of drying out, shrinkage crack etc.

Area of application:

- Waterproofing water retaining structures, terraces, roofs, basements, parapets, swimming pools, bathrooms and sunken portions of toilet blocks.
- General concrete repairs, Protection of concrete against corrosion and salt attack.

Direction of use:

- Remove all dirt and loose particles from the surface by wire brush.
- For best results, damp the surface before coating.
- Pour the CETCRETE LATEX one part of liquid into a suitable container.
- Add lumps free 2 part of cement to the above mix and mix for 2 to 4 minutes to obtain smooth, lump free slurry.
- Apply the mixed material with a stiff brush marking out the area apply like a paint.
- Keep stirring the mixed material to avoid setting during application and apply within 30 minutes after mixing.
- Apply second coat after 6 to 8 hour of first coat with other direction.

Coverage:

2 sq.mts. per kg in two coats depend upon application and surface.

Packing: Supplied in 500 g, 1 kg, 5 kg, 10 kg, 20 kg, 50 kg & 225 kg

Disclaimer: The product information & application details given by the company & its agents have been provided only as a general guideline for usage. No guarantee / warranty is given or implied with any recommendations made by us, our representatives or distributors, as the conditions of use and the competence of any labour involved in the application are beyond our control. The company does not assume any liability or consequential damage for unsatisfactory results, arising from the use of our products

Ashapura Minechem Ltd.

Head Office: Jeevan Udyog Building

3rd Floor, 278, D. N. Road, Fort

Mumbai -400 001 (India)

Email: info@ashapura.com | www.ashapura.com

Phone: Mumbai +91 22 6665 1700 | Ahmedabad 079 – 40063751 / 4

CIN No.: L14108MH1982PLC026396



Ashapura
Group Of Industries
Since 1960